

# **DATA SHEET**

TL 5-1044-18
Issue No.: 4
Uncontrolled printing

Effective from: 24.06.2023

# Waterproofing membrane FATRAFOL 810/V

# PRODUCT DESCRIPTION

**FATRAFOL 810/V** a waterproofing roof membrane made on the basis of PVCP reinforced with a polyester mesh. It is UV resistant and can be exposed to direct weathering.

# TECHNICAL PARAMETERS

Parameter	Standard	Value for assigned thickness			
		1.20 mm	1.50 mm	1.80 mm	2.00 mm
Visible defects	EN 1850-2	pass			
Straightness	EN 1848-2	≤ 50 mm			
Flatness	EN 1848-2	≤ 10 mm			
Mass per unit area	EN 1849-2	1.43 kg/m <sup>2</sup>   1.80 kg/m <sup>2</sup>   2.15 kg/m <sup>2</sup>   2.39 kg/m <sup>2</sup>			
Water tightness, 400 kPa	EN 1928	pass			
	method B				
Reaction to fire	EN 13501-1	class E			
Joint peel resistance	EN 12316-2	≥ 260 N/50 mm			
Joint shear resistance MD/CD	EN 12317-2	≥ 1000 N/50 mm / ≥ 1000 N/50 mm			
Maximum tensile force MD/CD	EN 12311-2	≥ 1000 N/50 mm / ≥ 1000 N/50 mm			
Elongation at maximum MD/CD	method A	≥ 15 % / ≥ 20 %			
tensile force					
Impact resistance	EN 12691	≥ 1000 mm ≥ 1250 mm			
	method A				
	EN 12691	≥ 2000 mm			
	method B				
Resistance to static load	EN 12730	≥ 20 kg			
	method B				
Tear resistance MD/CD	EN 12310-2	≥ 200 N / ≥ 220 N			
Rezistance to root penetration	EN 13948	Pass			
	FLL test				
Dimensional stability	EN 1107-2	± 0,3 %			
Foldability at low temperature	EN 495-5	≤ -25 °C			
Exposure to UV radiation,	EN 1297	Pass, grade 0			
elevated temperature and water					
(5000 h)					
Water vapour properties - moisture	EN 1931	$15000 \pm 30 \%$			
resistance factor μ					

MD - Machine Direction, CD - Cross Direction, Mass per unit area tolerance: -5 % / +10 %

#### APPROVALS / CERTIFICATES

- Declaration of performance and CE marking according to EN 13956:2012
- Classification of external fire performance according to EN 13501-5: Broof (t1), Broof (t2), Broof (t3), applicable for a particular composition of roof decks (test report on request)
- FM Approval for FATRAFOL 810/V Broof (t3), ID. 0003048015
- Environmental product declaration (EPD) according to ISO 14025

#### **DIMENSIONS**

Thickness [mm] (ČSN EN 1849-2)	<b>Width [mm]</b> (ČSN EN 1848-2)	<b>Length [m]</b> (ČSN EN 1848-2)	Quantity on the roll [m <sup>2</sup> ] *
1.20	1650	25	41.25
	2050	25	51.25
1.50	1650	20	33
	2050	20	41
1.80	1650	16,5	27,225
	2050	16,5	33.825
2.00	1650	15	24.75
	2050	15	30.75

The membrane can be produced in other dimensions upon agreement.

Thickness tolerance: -5%/+10%, width tolerance: -0.5%/+1%, length tolerance: -0%/+5%

#### **COLOUR AND APPEARANCE**

Standard colour of the top layer is light grey  $\sim$  RAL 7035. Other colours of the top layer: dark grey  $\sim$  RAL 7012, red  $\sim$  RAL 3016, blue  $\sim$  RAL 5015, white  $\sim$  RAL 9010, green  $\sim$  RAL 6000, white-grey  $\sim$  RAL 7047. The colour of the bottom layer is grey, for white membranes it can be grey or white. The colour shade of various production batches of the membranes may differ. Minor colour differences are not considered justified grounds for a claim.

FATRAFOL 810/V has smooth matt surface that is finely textured thanks to the reinforcing mesh.

### **USAGE**

FATRAFOL 810/V is designed for:

- mechanically fastened roof coverings
  - spot or linear fastening
  - gluing to anchor targets or inductive anchoring
- flat roofs with ballast/operation layer installed after some time has passed
- pitched or steep roofs with a ballast/operation layer
- other roof types with a ballast or operation layer, where it is more convenient to apply FATRAFOL 810/V instead of FATRAFOL 818 because of the small scale of the roof, logistics, or any other reasons

# **APPLICATION**

FATRAFOL 810/V can be laid on roofs only by specialised firms whose workers have been trained properly.

FATRAFOL 810/V is applied in compliance with the principles determined and described in the Construction and Technological Instruction FATRAFOL-S (PN 5415/2011), as amended at the time of the membrane's application, which is available at www.fatrafol.cz.

informative value

### **STORAGE**

Store at temperatures between -5 °C and +30 °C. On the site, it is necessary to protect the membrane against pollution. It is recommended to protect the membrane against weather effects until it is applied on the roof.

### **MORE INFORMATION**

For more information, please see the manufacturer's website www.fatrafol.cz.

### LEGAL CLAUSE

The technical data contained herein is based on our current knowledge and experience and relate to the use of the products under normal conditions for application. The information that is included in the current Technical Data Sheet is determined by the method of use and is incomplete. Before using this product, the user is obliged to check whether the product is suitable for the intended use. In addition to that, all users should contact the dealer or manufacturer of this product to obtain additional technical information regarding its use in case they are of the opinion that the information available to them requires some explanation, for both the standard and specific use of this product. Please always make sure that you have the latest version of the product's Technical Data Sheet at your disposal. This Data Sheet and additional information can be obtained from the sales or technical representative of the manufacturer or on the manufacturer's website.

#### **PRODUCER**

Fatra, a. s., třída Tomáše Bati 1541, 763 61 Napajedla, Czech Republic

tel.: +420 577 50 3325 (1111) e-mail: studio@fatrafol.cz http://www.fatrafol.cz





