



Confidential Report

Our Ref: 25/07974B-3/04/17



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 17 May 2017

Our Ref: 25/07974B-3/04/17

Your Ref:

Page: 1 of 8

Client:

Shaw Industries Group Inc.
Subsidiary Of Berkshire Hathaway
616E Walnut Avenue
Dalton
GA 30721
USA

Job Title:

Fire Test on One Sample of Carpet Tiles

Client's Order No:

Date of Receipt:

5 April 2017

Description of Sample(s):

One sample of carpet tiles referenced 5T227 Graph

Work Requested:

We were asked to make the following test(s):

BS EN 13501-1

* subcontracted test, UKAS accredited

** subcontracted test, EN ISO/IEC 17025 accredited

*** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.

Client: Shaw Industries Group Inc.

FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2010

Reaction to fire tests for building products – Part 2:

Ignitability when subjected to direct impingement of flame

Date of Test: 15/05/2017

Conditioning

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

Procedure

The sample was tested in accordance with BS EN ISO 11925-2:2010.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

1. If ignition occurs
2. Presence of flaming debris, if applicable
3. Ignition of the filter paper, if applicable

Duration of test

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.

Date: 17 May 2017

Our Ref: 25/07974B-3/04/17

Your Ref:

Page: 3 of 8

Client: Shaw Industries Group Inc.

Classification Criteria

The samples were classified according to BS EN 13501-1:2007+A1:2009 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification	
Classification	Criteria (mean values)
E _{FL}	F _s ≤ 150mm within 20 seconds
F _{FL}	None (No performance determined)

Flaming droplets / particles classification	
Classification	Criteria
No classification	Pass
d2	Fail (Ignition of paper)

Results

Specimen	Ignition (Yes or No)	Tip of flame reaches 150mm		Flaming droplets	
		Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)
Machine Direction	1	No	N/A	No	No
	2	No	N/A	No	No
	3	No	N/A	No	No
Across Machine Direction	1	No	N/A	No	No
	2	No	N/A	No	No
	3	No	N/A	No	No

Note

The specimens of floor covering were tested adhered to a 6mm fibre cement board , as defined in BS EN 13238:2010.

Date: 17 May 2017

Our Ref: 25/07974B-3/04/17

Your Ref:

Page: 4 of 8

Client: Shaw Industries Group Inc.

FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 15/05/2017

Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6 ± 1) mm and a density of $(1,800 \pm 200)$ Kg/m³ representing the standard substrate of Class A1fl or A2fl.

Procedure

The test was carried out in accordance with BS EN ISO 9239-1. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m² to 1.0 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.

Date: 17 May 2017

Our Ref: 25/07974B-3/04/17
Your Ref:

Page: 5 of 8

Client: Shaw Industries Group Inc.

Classification Criteria

The samples were classified according to BS EN 13501-1:2007+A1:2009 - Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m ²)
Bfl	8.0
Cfl	4.5
Dfl	3.0
	Smoke Production % x min
s1	≤ 750
s2	Not s1

When tested to BS EN ISO 11925-2:2010 the sample has to have a flame spread (Fs) of: $F_s \leq 150\text{mm}$ within 20 seconds (Class Efl).

Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.

Date: 17 May 2017

Our Ref: 25/07974B-3/04/17
 Your Ref:

Page: 6 of 8

Client: Shaw Industries Group Inc.

Results (Continued)

<u>Specimen No.</u>	<u>Direction of specimen</u>	<u>Smoke Obscuration</u>		<u>Maximum Flame front (mm)</u>	<u>Critical Heat Flux (kW/m²)</u>	<u>Duration of Flaming (sec)</u>
<u>Max %</u>	<u>% x min</u>					
1	Machine	13	64	242	8.2	1550
2	Across	24	122	245	8.1	1140
3	Across	27	110	250	8.0	1090
4	Across	26	137	245	8.1	900
Mean of 3 specimens	Across	26	123	247	8.0	1043

<u>Distance Burnt (mm)</u>	<u>Time for each specimen to burn (s)</u>			
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
50	220	240	265	185
100	350	360	335	249
150	600	461	473	351
200	766	600	555	575
250	---	---	720	---

Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested adhered to a 6mm fibre cement board , as defined in BS EN 13238:2010.Using Balls F41

Date: 17 May 2017

Our Ref: 25/07974B-3/04/17

Your Ref:

Page: 7 of 8

Client: Shaw Industries Group Inc.

Comments

In our opinion, based on the tests carried out on the sample supplied;

- a) the results of the BS EN ISO 11925-2:2010 test indicate the sample meets the requirements of a Class E_{FL}. It should be noted that this is only class that can be achieved when tested to this method alone.
- b) the results of the BS EN ISO 9239-1:2010 test indicate the sample meets the requirements of a Class B_{FL}-s1 when tested to this method alone.

Conclusion

In our opinion, the results indicate that the sample when classified to BS EN 13501-1:2007+A1:2009 meets an overall classification of: **Class B_{fl}-s1**.

Reported by:.....*B Marsden*..... B Marsden (Mrs), Fire Technician

Countersigned by:.....*P Doherty*..... P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.

Client: Shaw Industries Group Inc.

Uncertainty Budget - Annex

The uncertainty budget for BS EN 13501-1:2002 was determined as follows:-

Overall (BS EN ISO 9239-2)

The uncertainty varies, therefore:

At position between a Euroclass B to C $\pm 15\%$

At position between a Euroclass C to D $\pm 15.5\%$

At position between a Euroclass D to E $\pm 17.5\%$